King's Research Portal

DOI:

[10.1111/cid.12713](https://doi.org/10.1111/cid.12713)

Document Version

Peer reviewed version

[Link to publication record in King's Research Portal](#)

Citation for published version (APA):

Pichotano, E. C., de Molon, R. S., de Souza, R. V., Austin, R. S., Marcantonio-Jr, E., & Zandim-Barcelos, D. L. (2019). Evaluation of L-PRF combined with deproteinized bovine bone mineral for early implant placement after maxillary sinus augmentation: A randomized clinical trial. *Clinical Implant Dentistry and Related research*, 21(2), 253-262. <https://doi.org/10.1111/cid.12713>

Citing this paper

Please note that where the full-text provided on King's Research Portal is the Author Accepted Manuscript or Post-Print version this may differ from the final Published version. If citing, it is advised that you check and use the publisher's definitive version for pagination, volume/issue, and date of publication details. And where the final published version is provided on the Research Portal, if citing you are again advised to check the publisher's website for any subsequent corrections.

General rights

Copyright and moral rights for the publications made accessible in the Research Portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognize and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the Research Portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the Research Portal

Take down policy

If you believe that this document breaches copyright please contact librarypure@kcl.ac.uk providing details, and we will remove access to the work immediately and investigate your claim.

Title

Evaluation of L-PRF combined with deproteinized bovine bone mineral for early implant placement after maxillary sinus augmentation. A randomized clinical trial

Running Head

L-PRF and DBBM for early implant placement

Authors

Elton Carlos Pichotano DDS, MSc, PhD; Postdoctoral student, Department of Diagnosis and Surgery, School of Dentistry at Araraquara, Sao Paulo State University – UNESP, Araraquara, SP, Brazil

Rafael Scaf de Molon DDS, MSc, PhD; Postdoctoral student, Department of Diagnosis and Surgery, School of Dentistry at Araraquara, Sao Paulo State University – UNESP, Araraquara, SP, Brazil

Ricardo Violante de Souza DDS, MSc, PhD; Private Practice, School of Medicine of Ribeirao Preto, Sao Paulo University - USP, SP, Brazil.

Rupert S. Austin DDS, MSc, PhD; Professor, Tissue Engineering and Biophotonics, King's College London Dental Institute, Guy's Hospital, London, UK

Elcio Marcantonio-Jr DDS, MSc, PhD; Professor, Department of Diagnosis and Surgery, School of Dentistry at Araraquara, Sao Paulo State University – UNESP, Araraquara, SP, Brazil

Daniela Leal Zandim-Barcelos DDS, MSc, PhD; Professor, Department of Diagnosis and Surgery, School of Dentistry at Araraquara, Sao Paulo State University – UNESP, Araraquara, SP, Brazil

Corresponding Author

Daniela Leal Zandim-Barcelos DDS, MSc, PhD; Professor, Department of Diagnosis and Surgery, School of Dentistry at Araraquara, Sao Paulo State University – UNESP, Humaita 1680, 14801-903, Araraquara, Sao Paulo, Brazil; email: danielalzandim@foar.unesp.br

Conflict of Interest Statement:

The authors have no conflict of interest related to this study.

Author Contribution Statement:

- Elton C. Pichotano: Concept/Design, Data acquisition and interpretation, Drafting article, Critical revision of article, Approval of article
- Rafael S. de Molon: Concept/Design, Data analysis/interpretation, Drafting article, Critical revision of article, Approval of article, Statistics
- Ricardo V. de Souza and Rupert S. Austin: Concept/Design, Data acquisition and interpretation, Drafting article, Critical revision of article, Approval of article
- Elcio Marcantonio-Jr: Concept/Design, Data analysis/interpretation, Drafting article, Critical revision of article, Approval of article, Funding secured by
- Daniela L. Zandim-Barcelos: Concept/Design, Data analysis/interpretation, Drafting article, Critical revision of article, Approval of article, Statistics, Sample size calculation

All authors agree to be responsible for all aspects of the study in ensuring that questions related to the accuracy or integrity of any parts of the study are appropriately investigated and resolved.

ABSTRACT

Purpose: To investigate the effectiveness of adding leukocyte and platelet rich fibrin (L-PRF) to deproteinized bovine bone mineral (DBBM) for early implant placement after maxillary sinus augmentation.

Material and Methods: Twelve patients requiring two-stage bilateral maxillary sinus augmentation were enrolled to the study. The elevated sinus cavities were randomly grafted with DBBM + L-PRF (test) or DBBM alone (control) in a split-mouth design. Implants were placed in the augmented sites after 4 months in the test group and 8 months in the control group. Bone biopsies were collected during implant placement for histomorphometric evaluation. Resonance frequency analysis was performed immediately after implant placement in both groups. Cone-beam CT was obtained pre- and postoperatively for evaluation of graft volume changes.

Results: Both procedures were effective for maxillary sinus augmentation. CBCT analysis did not reveal differences in graft volume between test and control group at any of the evaluated time points ($P > 0.05$). Histological evaluation demonstrated increased percentage of newly formed bone for the test group ($44.58 \pm 13.9\%$) compared to the control group ($30.02 \pm 8.42\%$) ($P=0.0087$). The amount of residual graft in the control group was significantly higher ($13.75 \pm 9.99\%$) than in the test group (3.59 ± 4.22) ($P=0.0111$). Implant stability quotient (ISQ) immediately after implant placement was significantly higher in the control group (75.13 ± 5.69) compared to the test group (60.9 ± 9.35) ($P=0.0003$). The ISQ values at loading did not differ between the groups ($P=0.8587$). Implant survival rate was 100% for both groups.

Conclusion: The addition of L-PRF to the DBBM into the maxillary sinus allowed early implant placement (4 months) with increased new bone formation than DBBM alone after 8 months of healing.

KEYWORDS: Alveolar bone; bone substitutes, cone-beam computed tomography, dental implants, maxillary sinus; platelet-rich plasma; sinus floor augmentation.

1 INTRODUCTION

The posterior region of the maxilla is associated with several challenges regarding successful dental implant rehabilitation due to reduced bone quality and ridge resorption caused by sinus pneumatization after tooth loss.¹ Different approaches for treatment of severely resorbed posterior maxilla have been performed using onlay bone grafts,² interpositional grafts after maxillary osteotomy³ and sinus augmentation procedures.⁴ Sinus lifting with the lateral technique, initially described by Boyne and James⁵ and established by Tatum,⁶ is the most commonly used approach to augment the maxillary sinus, which allow the installation of dental implants in the severely resorbed posterior maxilla. The implant survival rate, placed immediately or in two-stage approach, after sinus lifting is higher than 95% according to a recent systematic review with meta-analysis⁷ and with several retrospective studies,⁸⁻¹¹ over a period of at least 5-years of follow-up, and the complication rate are minimal. Furthermore, different graft materials, such as autogenous,¹² xenogenous,¹³ alloplastic and the combination of bone grafts and growth factors can be safely used during maxillary sinus augmentation.^{14, 15} Indeed, this technique has become a routine treatment modality over the years with highly predictability and effectiveness.

Demineralized bovine bone mineral (DBBM) is a biocompatible material with osteoconductive properties¹⁶ that has been frequently used for maxillary sinus augmentation. This biomaterial possesses several advantages compared to the autogenous bone, such as unlimited availability, low resorption rate and reduced morbidity to the

patient. As well as the autogenous bone, the risk of immunological rejection of DBBM is minimum and a high clinical success rate has been observed with its use.⁹ DBBM act as a scaffold allowing osteogenic cell migration from the maxillary sinus to the graft particles permitting the apposition of de novo bone formation.^{14, 17, 18} However, DBBM compared to the autogenous bone, lacks the osteogenic and osteoinductive properties, and the maturation of this type of material may take up to 8 months¹⁹ before implants can be safely installed in maxillary sinus, which might be considered a disadvantage of this material. To overcome this concern, several studies have investigated the addition of growth factors to grafting material aiming at enhance bone neoformation and accelerates graft maturation.^{1, 18-32}

Leukocyte and platelet rich fibrin (L-PRF), first described by Dohan et al.³³ is an autogenous biomaterial containing several growth factors.^{1, 18, 19, 25} L-PRF, a second-generation of platelet concentrates, is basically made of concentrated autologous platelets as well as leukocytes and cytokines.³⁴ It has been demonstrated that L-PRF activates the vascular system by promoting angiogenesis, and also by releasing several growth factors involved in soft and hard tissue healing.^{30, 35} Additionally, previous studies demonstrated that L-PRF is capable of inducing bone regeneration^{22, 36} and fibroblast proliferation,³⁷ thus improving and accelerating tissue healing,³⁵ and enhancing implant stability.³⁰ To obtain L-PRF, the patient's blood is collected through venipuncture without anticoagulant or additives, and is immediately centrifuged. After processing, a natural fibrin clot is localized in the middle of the tube. The fibrin clot can than be compressed to obtain a membrane. From each fibrin clot, one L-PRF membrane is obtained. The L-PRF membranes can either be cut into small pieces and mixed with DBBM or autogenous bone, or be used as a membrane¹⁸ It is a safe, and cost-effective technique to improve repair following surgery.²⁴ Due to its dense fibrin fiber network with strong mechanical

characteristics,⁸ it can act as a scaffold for a number of cell types and provide support for mesenchymal stem cells.³⁸

Since growth factors play an important role in tissue regeneration, the present study aimed to investigate the effects of L-PRF to accelerate bone formation after maxillary sinus augmentation combined with DBBM as the graft material, and the outcomes of early placement of dental implants after sinus augmentation. The study was set up to test the hypothesis that the addition of L-PRF to DBBM would enhance new bone formation and graft maturation, thereby allowing faster implant placement. Graft volume dimensional changes, bone and soft tissue characteristics and implant stability were investigated using cone-beam computed tomography (CBCT), histology and RFA analysis, respectively.

2 MATERIALS AND METHODS

This prospective, double-blinded, randomized-controlled clinical trial was accompanied in accordance with the Consolidated Standards of Reporting Trials (CONSORT) Statement.³⁹ The study protocol was approved by the Ethical Committee on Human Research (CAAE #41357514.5.0000.5416) before patient enrolment and was registered in the Brazilian Registry of Clinical Trials (ReBEC - RBR-95m73t). All patients were informed about the surgical procedures and written informed consent was obtained from all subjects.

This randomized clinical trial was designed as a split-mouth study. Bilateral maxillary sinuses were randomly assigned to either the test (DBBM + L-PRF) or the control (DBBM) group.

2.1 Sample size calculation

The minimum sample size calculation for this study was calculated using G*Power 3.1.⁴⁰ Considering a standard deviation of 5.0% for the primary outcome (percentage of newly formed bone) and a mean difference of 5.5% between the test and control groups, an effect size of 1.1 was obtained. The effect size was calculated based on previous data.⁴¹ Using this effect size with a given alpha level of 0.05, a power of 80% and an allocation ratio of 1, a sample size of 11 patients per group was calculated.²⁸

2.2 Patients

Patients were recruited at the Department of Diagnosis and Surgery of the School of Dentistry at Araraquara – UNESP from December 2014 through May 2015. The inclusion criteria were as follows: patients who required bilaterally sinus floor augmentation for implant installation in the posterior maxillary region with residual bone height of < 4 mm (based on CBCT). The exclusion criteria were: compromised general healthy condition, smokers or ex-smokers, alcohol and drug abusers, irradiated patients, pregnancy, therapies with bisphosphonates and immunosuppressives,⁴² blood platelet disorders, chronic sinusitis, patients suffering from any pathology in the maxillary sinus, and uncontrolled diabetes.⁴³

2.3 PRF preparation

The L-PRF membranes were prepared according to the technique described by Dohan et al.³³ Venous blood samples were taken at the beginning of the procedure using vacutainers (BD, Franklin Lakes, NJ, USA) and centrifuged for 10 minutes at 300 g (3000 rpm) (Kasvi K14-0815, Curitiba, PR, Brazil). After centrifugation, a natural fibrin clot was present in the middle of the tube, between the acellular plasma at the top and the red

corpuscle at the bottom. Each fibrin clot was removed from the tube and placed in a metal box (Xpression, Intra-lock System, Sao Paulo, Brazil). The fluids present in the fibrin clots were squeezed out to obtain L-PRF membranes.

2.4 Sinus augmentation procedure

The surgical procedures were performed as described earlier.^{12, 13, 44} Briefly, patients received local anesthesia (Articaine 4% and epinephrine 1:100,000; DFL, Rio de Janeiro, RJ, Brazil) followed by a mid-crestal and vertical releasing incisions along the residual alveolar bone to expose the lateral sinus wall. A lateral window approach was performed to access the sinus wall using diamond round bur. The surgical access respected the position of implant placement planning and the maxillary sinus anatomy.

After carefully sinus membrane elevation, the control side was filled with small particles (0.25-1 mm) of DBBM (Bio-Oss®, Geistlich Pharma AG, Wolhusen, Switzerland), while the test side was filled with a mixture of L-PRF membranes and DBBM (0.25-1 mm). For each membrane of L-PRF (4-5 mL) cut in few fragments, 0.5g of Bio-Oss® was mixed. The graft materials were gently compacted at the sinus cavity. A resorbable collagen membrane (Bio-Gide®, Geistlich Pharma AG, Wolhusen, Switzerland) was used to cover the lateral window after graft placement, and then the soft tissues were sutured.

The surgical procedures were performed by a single experienced surgeon (ECP). The bilateral maxillary sinuses were randomly assigned by means of a computer-generated randomization list to either the test (DBBM + L-PRF) or the control group (DBBM). The numbers were sealed in opaque envelopes by a person not involved in the study. The surgeon was blinded to the graft material applied to each sinus cavity before graft implantation. After sinus membrane elevation, the envelope containing the treatment

indication was opened by the surgeon assistant. The patients were not informed of the assigned materials.

After surgery, the patients received postoperative instructions for appropriate oral hygiene control and treatment with an oral antibiotic (amoxicillin, 500 mg three times a day for a week), an oral anti-inflammatory (nimesulide, 100 mg twice a day for 5 days), and an analgesic (paracetamol, 750 mg every 6 hours for 2 days). They were advised to rinse their mouth with chlorhexidine (0.2%) daily for 14 days. The sutures were removed seven days after the surgical procedure, and the area was not subjected to any direct loading during the entire bone regeneration phase.

2.5 Implant placement

After four months (test group) and eight months (control) of healing, dental implants were placed in both augmented maxillary sinuses. The implants (TitamaxTi EX ACQUA, Neodent, Curitiba, Brazil) were placed according to the manufacturer's protocol.

2.6 Radiographic analysis

Each patient underwent four CBCT scans (SCANORA® 3Dx, Soredex, Tuusula, Finland): preoperative (T0), immediately after maxillary sinus augmentation (T1), after four months (T2 for test group) and eight months (T2 for control group) post-maxillary sinus augmentation. The following parameters were used for all scans: 10 mAs, 90 kVp and a 20 s scan time using a nine-inch field of view (FOV). The preoperative scan was used to evaluate the sinus anatomy and the residual alveolar ridge for implant placement in a two-stage surgery. The scan immediately after augmentation was performed seven days after the surgery. The four-month post augmentation scan was performed in the test group before implant placement. The eight-month scan was performed in the control

group prior to implant surgery. The raw data of the scans were reconstructed and exported in DICOM file format and imported into CBCT interpretation software (Planmeca Romexis 3D, Planmeca Oy, Helsinki, Finland).

The volumetric measurements (in cm³) of the grafts were taken using 1 mm sagittal sections by assessing the differential hyperdensity color of the images. The volumetric dimensions were automatically calculated by the Planmeca software and represented in cubic centimeters. One maxillofacial radiologist experienced with CBCT that had received prior training in Planmeca software performed all volumetric measurements in a standardized manner.

2.7 Histology and histomorphometric analysis

During implant site preparation, bone biopsies were harvested from the maxillary sinus with the aid of a trephine drill (3i Implant Innovations, Florida, FL, USA.) (3.0 mm in diameter and 15 mm in length). Two-bone biopsies cylinders were obtained per patient (one for each sinus) and the trephine sites were used for implant placement. The biopsy involved the residual maxillary bone and augmented sinus (bone graft), and preparation depth was defined from the planned implant length. After biopsies removal, the implants were placed in all patients.

Biopsies were immediately fixed in 10% buffered formaldehyde solution for 3 days and then processed, as described by de Molon et al. (2015).¹² Serial sections of 6- μ m thickness were obtained from each specimen parallel to the long axis of the cylindrical core using an automatic microtome (Jung Supercut 2065, Leica Instruments GmbH, Heidelberg, Germany). The sections were mounted on slides and stained with hematoxylin and eosin (H/E). The histological evaluation was performed using an optical microscope (Diastar; Leica microsystems GmbH, Wetzlar, Germany) at 100-x

magnification. Images were selected and transferred to a computer display through a digital camera attached to an optical microscope (DFC-300-FX, Leica microsystems GmbH, Wetzlar, Germany) allowing for histomorphometric analysis.

Two blinded examiners performed the histomorphometric analysis. The digital images of histological slides were imported and analyzed using the system Image J for Windows (Image J 1.45; Wayne Rasband, National Institutes of Health, USA). The histomorphometric analysis was performed to measure newly formed bone, residual bone graft and fibrous tissue after four months (test group) or eight months (control group) of sinus augmentation. The measurements were also expressed as percentages of the total measured area.

2.8 Resonance frequency analysis

The implant stability quotient (ISQ) was measured with a RFA device (Osstell; Integration Diagnostics, Gothenburg, Sweden). SmartPegs were used to measure the implant stability immediately after implant placement, and at the moment of prosthetic loading in both groups. The measurements were performed in two directions, buccal-lingual and mesio-distal, and the mean values were used.¹³ The ISQ measurements were performed in a standardized manner by one experienced examiner, who was masked to the treatment protocol.

2.9 Statistical analysis

Statistical analysis was performed using GraphPad Prism software (version 6.0, GraphPad Software, Inc., La Jolla, CA, USA). All data are expressed as the mean $\pm$ the standard error of the mean (SEM). All data were submitted to the D'Agostino & Pearson normality test to assess the normality of the data distribution. Histomorphometric, volumetric and ISQ measurements were compared within each patient (test versus

control) using paired t-tests. The differences between the graft volume at time T1 and T2 for both groups were also analyzed using paired t-tests. Differences were considered significant at $P < 0.05$.

3 RESULTS

3.1 Patient characteristics

A total of 12 patients were enrolled in this study (Fig. 1); 6 patients were male and 6 were female, and they ranged in age from 43 to 63 years (with mean age of 54.17 ± 6.95 years). Eight patients were partially edentulous and 4 patients were totally edentulous in the upper jaw (Table 1). 38 implants were placed in the augmented sites, 19 in the control group and 19 in the test group (Table 1). During the healing period, the patients did not wear any provisional removable dentures. All implants had the same diameter (4 mm) and length (11 mm). No complications were observed during or after the sinus augmentation procedure. No perforation of the sinus membrane was observed, and no complications such as migration of the graft material or opening of wound edges were observed in the test or control groups. The survival rate of the implants placed in the augmented maxillary sinus area 12 months after loading was 100% for both groups.

3.2 Cone-beam computed tomography analysis

To evaluate the repeatability of the measurements, the Pearson correlation coefficient (r) was calculated in the differences of the three measurements in five samples with an r -value of 0.995 ($P < 0.001$). A total of 24 CBCT scans were taken from 12 patients to evaluate graft volume changes after maxillary sinus augmentation.

The results of the CBCT analysis are described in Table 2. The mean graft volume observed immediately after sinus augmentation (T1) for the test ($1.68 \pm 0.42 \text{ cm}^3$) and

control ($1.46 \pm 0.53 \text{ cm}^3$) groups was not statistically different. After four months of healing (T2), the mean graft volume in the test group lowered to $1.10 \pm 0.25 \text{ cm}^3$. A reduction in the mean graft volume was also observed in the control group after eight months of healing ($T2=0.91 \pm 0.35 \text{ cm}^3$). Differences in graft volume between the two time points in each group were statistically significant ($P<0.0001$ for the test and $P=0.0002$ for the control group). After four months of healing, a significant reduction in the graft volume could be observed for the test group ($33.14 \pm 10.74\%$). Similar result was noted for the control group after eight months of healing ($36.71 \pm 15.81\%$). The comparison of the rate of resorption between the groups did not show statistically significant difference. In both groups, the augmented bone presented adequate volume for implant placement.

3.3 Bone histomorphometry analysis

Immediately before implant placement, bone biopsies were collected from the maxillary sinus on both sides for a descriptive and histomorphometric analysis (Fig. 2). Our findings revealed a statistically significant increase ($P=0.0083$) in the amount of newly formed bone between the test group ($2.35 \pm 0.73 \text{ mm}^2$) and the control group ($1.58 \pm 0.44 \text{ mm}^2$). Consequently, the percentage of new bone formation was significantly increased ($P=0.0087$) in the test group ($44.58 \pm 13.9\%$) compared to the control group ($30.02 \pm 8.42\%$) (Table 3).

A significant higher ($P=0.0104$) amount of residual graft material was found in the control group ($0.71 \pm 0.51 \text{ mm}^2$) than in the test group ($0.18 \pm 0.22 \text{ mm}^2$). As expected, the percentage of bone graft in the control group ($13.75 \pm 9.99\%$) was also greater ($P=0.0111$) than in the test group ($3.59 \pm 4.22\%$). Regarding the amount of fibrous tissue in the maxillary sinus cavity, the data demonstrated no significant differences between

groups. The control group showed a slight increase in the amount of fibrous tissue ($1.61 \pm 0.65 \text{ mm}^2$) compared to the test group ($1.40 \pm 0.59 \text{ mm}^2$). Similarly, the percentage of fibrous tissue was also not different between groups ($30.64 \pm 12.46\%$ and $26.60 \pm 11.13\%$ for the control and test groups, respectively) (Table 3).

3.4 Resonance frequency analysis

ISQ was measured immediately after implant placement four and eight months after sinus augmentation for the test and control group, respectively. Moreover, at the time of implant loading, RFA was measured again. All implants evaluated in both groups demonstrated high ISQ values. The results showed significantly higher ($P=0.0003$) ISQ values after implant placement in the control group (75.13 ± 5.69) than in the test group (60.90 ± 9.35) (Table 4). However, at the time of implant loading a significant increase in ISQ was observed in the test group (60.9 ± 9.35 to 76.08 ± 5.86 , $P=0.0014$). No differences were observed between groups at loading (Table 4).

4 DISCUSSION

In this study, we hypothesized that the addition of L-PRF to DBBM would enhance new bone formation and regeneration, allowing faster implant placement after maxillary sinus augmentation. We used different methodologies to evaluate graft volume changes, bone characteristics and implant stability, i.e. CBCT, histology and RFA analyses. Our results demonstrate that there was no differences related to graft volume changes between groups immediately after graft placement and after the healing period of four and eight months for the test and control group, respectively. However, a significant decrease in graft volume between the two time points (baseline and after healing time) was observed for both groups. Interestingly, the amount of newly formed bone was significantly increased

when L-PRF was added to the graft, compared to the control group. As expected, the amount of residual graft was significantly higher in the control group compared to the test group, and no differences were observed between groups regarding the amount of fibrous tissue. Finally, ISQ values were significantly higher in the control group compared to the test group; however for both groups, safe ISQ values were found, which enabled implant osseointegration even as soon as four months after surgery in the L-PRF group. Moreover, ISQ at loading for the test group showed significant increase, which was similar to the control group.

The ideal time for implant placement is dependent of several aspects mainly related to the recipient area, socket dimension, bone quality and quantity, and time required for partial or complete tissue healing.⁴⁵ Autogenous bone possesses several advantages because of its osteogenic, osteoinductive and osteoconductive properties.¹³ However, the limited availability of this tissue and morbidity during graft removal are drawbacks related to this approach.⁴⁶ Consequently, the use of biomaterials to fill the maxillary sinus is necessary. In this context, DBBM is a widely used biomaterial due to its similarity to the human bone, and high rate of clinical success.⁴⁷ Nevertheless, DBBM lacks the osteogenic properties acting mainly as a scaffold for new bone formation. Importantly, the maturation of this type of material may take up to 8 months¹⁹ before implants can be safely placed in maxillary sinus, which might be considered a disadvantage of this material. To mitigate this shortcoming, the addition of growth factors, particularly L-PRF, to the graft material has been suggested as an alternative approach to increase bone formation, enhance implant stability, favor osseointegration, and accelerate tissue maturation and healing.^{1, 18, 21, 22, 28-30, 34, 35, 44, 45, 47-52}

CBCT is considered a reliable technique for the 3D visualization of graft volume changes after sinus augmentation. In this study, we performed three different CBCTs at

different time points: immediately after the bone graft, and after four and eight months of healing. Our results did not reveal any statistically significant differences between the groups regarding graft volume changes. Comparing the measured volumes one week after sinus augmentation with those measures after four (test group) or eight (control group) months of healing, a significant volume loss was observed in both groups. The mean percentage of volume loss was 33.14% for the test group (DBBM + L-PRF) and 36.71% for the control group (DBBM only). These variations in the volumetric changes were also observed in previous studies.⁵³⁻⁵⁵ Accordingly, previous studies have demonstrated that the mean volume reduction of DBBM in the maxillary sinus ranges from 15.2 to 21.5%.³⁷ The disparities found in the literature in regard to the dimensional changes could be influenced by the residual alveolar ridge, maxillary sinus anatomy, amount of grafted material into the sinus, and compression force during graft placement.^{53, 56, 57}

The maturation time for implant placement after sinus augmentation with DBBM may take several weeks to form new bone, or close to eight months of healing for safe implant installation.^{19, 58} This fact could be closely related, despite of the graft characteristics, to the graft volume. Consequently, a larger DBBM graft volume requires more time before implant loading.⁵⁹ In the current study, the amount of DBBM was reduced in the test group since L-PRF was added to the graft material. The area ($0.71 \pm 0.51 \text{ mm}^2$ control group; $0.18 \pm 0.22 \text{ mm}^2$ test group) and percentage ($13.75 \pm 9.99\%$ control group and $3.59 \pm 4.22\%$ for test group) of graft material was statistically higher in the control group compared to the test group. Furthermore, L-PRF contains dense fibrin fiber network that helps to avoid the small particles of DBBM from dispersing. This means that less amount of graft material is needed to fill the maxillary sinus to obtain a sufficient vertical bone height for appropriate implant length installation.⁵⁹ Moreover, the fibrin fiber has a positive impact on handling and facilitates adhesion to the bone defect

walls.⁶⁰ Paralleling recent observations,⁵⁹ our findings indicate that L-PRF can act as a delivery system for DBBM particles during sinus lifting. On the other hand, Nizan et al.²⁸ did not observe any additional benefit of L-PRF on bone formation after six months of sinus augmentation. Corroborating these clinical findings, recent studies showed similar results when adding L-PRF to the graft materials into the maxillary sinus, i.e., no beneficial effect on regeneration and new bone formation.^{61, 62} In these studies, the long graft-healing time did not allow them to verify potential effect of L-PRF in accelerating bone formation.

To investigate the implant stability, RFA analysis was performed immediately after implant placement for both groups by measuring the ISQ as a function of stiffness of the bone-implant interface.^{13, 63} This measurement is affected by innumerable factors, such as the healing time, bone quality and density, firmness of the fixation, degree of osseointegration, hardness of the bone, and the implant height above the alveolar crest.⁶⁴ ⁶⁶ It was previously pointed out that ISQ values ranging from 57 to 82 denote appropriate implant stability and a complete process of osseointegration.⁶⁷ In the current study, the control group showed statistically higher ISQ values compared to the test group (75.13 ± 5.69 ; and 60.90 ± 9.35 for the control and test group, respectively). This outcome might be attributed to the difference in the healing time between both groups. According to a previous study,³¹ ISQ values after sinus augmentation utilizing L-PRF progressively increase over time, meaning that the time for implant healing play a crucial role for increased secondary implant stability. This was confirmed in our studies because the ISQ values at loading demonstrated a significant increase in the test group compared to the initial value immediately at implant placement (60.90 ± 9.35 and 76.08 ± 5.86). Recent observations have demonstrated that the addition of L-PRF improves implant stability and allows for faster osseointegration.⁵² The difference between our study and their study

might be accounted by the implant site (posterior vs. anterior), differences in bone quality, and healing period (baseline, one and four weeks of healing). The present data suggest that a site undergoing sinus augmentation with DBBM + L-PRF can offer sufficient implant stability, decreasing the necessary time for bone graft maturation and allowing earlier implant placement.

The outcomes of the current investigation proved the null hypothesis. It was demonstrated that the addition of L-PRF into the maxillary sinus resulted in increased amount of newly formed bone compared to the control group. Moreover, L-PRF seems to accelerate bone graft maturation allowing early implant placement after sinus augmentation.

An important consideration should be mentioned when interpreting the present outcomes. One limitation of this investigation is that the groups (test and control) were compared to a different time points (eight months for the control and four months for the test group). With this experimental design, it was not possible to confirm if there would be more new bone in the control group if we had gone in earlier to place the implants. Current literature^{28, 62} shown that a healing period of at least six months is necessary before implants can be safely placed in the grafted sinus with Bio-Oss, and for this reason our studies have focused in two different times points of evaluation. The platelet quantification in total blood was not performed. Therefore, we could not determine whether the patient variability platelets concentration may have influenced our findings.

In addition, an interesting caveat that our studies did not address is whether the bone graft maturation would have changed if the dimensions of the maxillary sinus and the amount of biomaterial used were measured during the surgical procedures. We believe that the amount of biomaterial in the control group was higher compared to the test group, since the L-PRF membranes increase the graft volume. Thus, less bone graft material was

placed in the test group compared to the control. For all those reasons, further randomized clinical trials are warranted before definitive conclusions about the use of L-PRF can be drawn. Our data, despite the inherent limitations related, pointed out to important aspects and encourage earlier intervention in the maxillary sinus grafted with DBBM + L-PRF allowing fast graft maturation and implant placement.

5 CONCLUSION

Taken together, our data demonstrated that the addition of L-PRF to the DBBM graft increased the newly formed bone after 4 months of healing. The residual graft material was statistically lower in the test group, which might have influenced the early maturation of the bone graft. Collectively, our findings suggest that L-PRF lead to faster bone graft maturation, and this outcome might suggest sinus augmentation with a shorter healing time before implant placement.

ACKNOWLEDGEMENTS

The authors are extremely grateful to Geistlich Pharma AG (Wolhusen, Switzerland) for free donation of Bio-Oss® and Geistlich BioGide regenerative membranes, and Neodent (Implant system, Curitiba, PR, Brazil) for the donation of the implants. The authors would also like to thank Dr. Bethan Thomas, Consultant Maxillofacial radiologist for advice on the interpretation of the CBCT images. ECP was supported by grant provided by CAPES (Coordenacao de Aperfeicoamento de Pessoal de Nivel Superior).

REFERENCES

1. Ali S, Bakry SA, Abd-Elhakam H. Platelet-Rich Fibrin in Maxillary Sinus Augmentation: A Systematic Review. *J Oral Implantol* 2015; **41**: 746-753.

2. Cordaro L, Torsello F, Accorsi Ribeiro C, Liberatore M, Mirisola di Torresanto V. Inlay-onlay grafting for three-dimensional reconstruction of the posterior atrophic maxilla with mandibular bone. *Int J Oral Maxillofac Surg* 2010; **39**: 350-357.
3. Pelo S, Gasparini G, Moro A, Boniello R, Amoroso PF. Segmental Le Fort I osteotomy with bone grafting in unilateral severely atrophied maxilla. *Int J Oral Maxillofac Surg* 2009; **38**: 246-249.
4. Chiapasco M, Casentini P, Zaniboni M. Bone augmentation procedures in implant dentistry. *Int J Oral Maxillofac Implants* 2009; **24 Suppl**: 237-259.
5. Boyne PJ, James RA. Grafting of the maxillary sinus floor with autogenous marrow and bone. *J Oral Surg* 1980; **38**: 613-616.
6. Tatum H, Jr. Maxillary and sinus implant reconstructions. *Dent Clin North Am* 1986; **30**: 207-229.
7. Starch-Jensen T, Aludden H, Hallman M, Dahlin C, Christensen AE, Mordenfeld A. A systematic review and meta-analysis of long-term studies (five or more years) assessing maxillary sinus floor augmentation. *Int J Oral Maxillofac Surg* 2018; **47**: 103-116.
8. Tetsch J, Tetsch P, Lysek DA. Long-term results after lateral and osteotome technique sinus floor elevation: a retrospective analysis of 2190 implants over a time period of 15 years. *Clin Oral Implants Res* 2010; **21**: 497-503.
9. Lutz R, Berger-Fink S, Stockmann P, Neukam FW, Schlegel KA. Sinus floor augmentation with autogenous bone vs. a bovine-derived xenograft - a 5-year retrospective study. *Clin Oral Implants Res* 2015; **26**: 644-648.
10. Maddalone M, Mirabelli L, Venino PM, Karanxha L, Porcaro G, Del Fabbro M. Long-term stability of autologous bone graft of intraoral origin after lateral sinus floor

elevation with simultaneous implant placement. *Clin Implant Dent Relat Res* 2018; **20**: 713-721.

11. Khoury F, Keller P, Keeve PL. Stability of Grafted Implant Placement Sites After Sinus Floor Elevation Using a Layering Technique: 10-Year Clinical and Radiographic Results. *Int J Oral Maxillofac Implants* 2017; **32**: 1086-1096.

12. de Molon RS, de Paula WN, Spin-Neto R, Verzola MH, Tosoni GM, Lia RC, Scaf G, Marcantonio E, Jr. Correlation of fractal dimension with histomorphometry in maxillary sinus lifting using autogenous bone graft. *Braz Dent J* 2015; **26**: 11-18.

13. Dos Anjos TL, de Molon RS, Paim PR, Marcantonio E, Marcantonio E, Jr., Faeda RS. Implant stability after sinus floor augmentation with deproteinized bovine bone mineral particles of different sizes: a prospective, randomized and controlled split-mouth clinical trial. *Int J Oral Maxillofac Surg* 2016; **45**: 1556-1563.

14. Browaeys H, Bouvry P, De Bruyn H. A literature review on biomaterials in sinus augmentation procedures. *Clin Implant Dent Relat Res* 2007; **9**: 166-177.

15. Scarano A, Piattelli A, Perrotti V, Manzon L, Iezzi G. Maxillary sinus augmentation in humans using cortical porcine bone: a histological and histomorphometrical evaluation after 4 and 6 months. *Clin Implant Dent Relat Res* 2011; **13**: 13-18.

16. Kazemi E, Dadfarnia S, Haji Shabani AM, Ranjbar M. Synthesis, characterization, and application of a Zn (II)-imprinted polymer grafted on graphene oxide/magnetic chitosan nanocomposite for selective extraction of zinc ions from different food samples. *Food Chem* 2017; **237**: 921-928.

17. Tadjoeidin ES, de Lange GL, Bronckers AL, Lyaruu DM, Burger EH. Deproteinized cancellous bovine bone (Bio-Oss) as bone substitute for sinus floor

elevation. A retrospective, histomorphometrical study of five cases. *J Clin Periodontol* 2003; **30**: 261-270.

18. Bolukbasi N, Ersanli S, Keklikoglu N, Basegmez C, Ozdemir T. Sinus Augmentation With Platelet-Rich Fibrin in Combination With Bovine Bone Graft Versus Bovine Bone Graft in Combination With Collagen Membrane. *J Oral Implantol* 2015; **41**: 586-595.

19. Choukroun J, Diss A, Simonpieri A, Girard MO, Schoeffler C, Dohan SL, Dohan AJ, Mouhyi J, Dohan DM. Platelet-rich fibrin (PRF): a second-generation platelet concentrate. Part V: histologic evaluations of PRF effects on bone allograft maturation in sinus lift. *Oral Surg Oral Med Oral Pathol Oral Radiol Endod* 2006; **101**: 299-303.

20. Angelo T, Marcel W, Andreas K, Izabela S. Biomechanical Stability of Dental Implants in Augmented Maxillary Sites: Results of a Randomized Clinical Study with Four Different Biomaterials and PRF and a Biological View on Guided Bone Regeneration. *Biomed Res Int* 2015; **2015**: 850340.

21. Boora P, Rathee M, Bhorla M. Effect of Platelet Rich Fibrin (PRF) on Peri-implant Soft Tissue and Crestal Bone in One-Stage Implant Placement: A Randomized Controlled Trial. *J Clin Diagn Res* 2015; **9**: ZC18-21.

22. Castro AB, Meschi N, Temmerman A, Pinto N, Lambrechts P, Teughels W, Quirynen M. Regenerative potential of leucocyte- and platelet-rich fibrin. Part B: sinus floor elevation, alveolar ridge preservation and implant therapy. A systematic review. *J Clin Periodontol* 2017; **44**: 225-234.

23. Chang IC, Tsai CH, Chang YC. Platelet-rich fibrin modulates the expression of extracellular signal-regulated protein kinase and osteoprotegerin in human osteoblasts. *J Biomed Mater Res A* 2010; **95**: 327-332.

24. Davis VL, Abukabda AB, Radio NM, Witt-Enderby PA, Clafshenkel WP, Cairone JV, Rutkowski JL. Platelet-rich preparations to improve healing. Part I: workable options for every size practice. *J Oral Implantol* 2014; **40**: 500-510.
25. Davis VL, Abukabda AB, Radio NM, Witt-Enderby PA, Clafshenkel WP, Cairone JV, Rutkowski JL. Platelet-rich preparations to improve healing. Part II: platelet activation and enrichment, leukocyte inclusion, and other selection criteria. *J Oral Implantol* 2014; **40**: 511-521.
26. Del Corso M, Mazor Z, Rutkowski JL, Dohan Ehrenfest DM. The use of leukocyte- and platelet-rich fibrin during immediate postextractive implantation and loading for the esthetic replacement of a fractured maxillary central incisor. *J Oral Implantol* 2012; **38**: 181-187.
27. Jung RE, Schmoekel HG, Zwahlen R, Kokovic V, Hammerle CH, Weber FE. Platelet-rich plasma and fibrin as delivery systems for recombinant human bone morphogenetic protein-2. *Clin Oral Implants Res* 2005; **16**: 676-682.
28. Nizam N, Eren G, Akcali A, Donos N. Maxillary sinus augmentation with leukocyte and platelet-rich fibrin and deproteinized bovine bone mineral: A split-mouth histological and histomorphometric study. *Clin Oral Implants Res* 2017.
29. Ocak H, Kutuk N, Demetoglu U, Balcioglu E, Ozdamar S, Alkan A. Comparison of Bovine Bone-Autogenic Bone Mixture Versus Platelet-Rich Fibrin for Maxillary Sinus Grafting: Histologic and Histomorphologic Study. *J Oral Implantol* 2017; **43**: 194-201.
30. Oncu E, Erbeyoglu AA. Enhancement of Immediate Implant Stability and Recovery Using Platelet-Rich Fibrin. *Int J Periodontics Restorative Dent* 2017.
31. Tabrizi R, Arabion H, Karagah T. Does platelet-rich fibrin increase the stability of implants in the posterior of the maxilla? A split-mouth randomized clinical trial. *Int J Oral Maxillofac Surg* 2017.

32. Tajima N, Ohba S, Sawase T, Asahina I. Evaluation of sinus floor augmentation with simultaneous implant placement using platelet-rich fibrin as sole grafting material. *Int J Oral Maxillofac Implants* 2013; **28**: 77-83.
33. Dohan DM, Choukroun J, Diss A, Dohan SL, Dohan AJ, Mouhyi J, Gogly B. Platelet-rich fibrin (PRF): a second-generation platelet concentrate. Part I: technological concepts and evolution. *Oral Surg Oral Med Oral Pathol Oral Radiol Endod* 2006; **101**: e37-44.
34. Oncu E, Kaymaz E. Assessment of the effectiveness of platelet rich fibrin in the treatment of Schneiderian membrane perforation. *Clin Implant Dent Relat Res* 2017; **19**: 1009-1014.
35. Oncu E, Bayram B, Kantarci A, Gulsever S, Alaaddinoglu EE. Positive effect of platelet rich fibrin on osseointegration. *Med Oral Patol Oral Cir Bucal* 2016; **21**: e601-607.
36. Marx RE, Carlson ER, Eichstaedt RM, Schimmele SR, Strauss JE, Georgeff KR. Platelet-rich plasma: Growth factor enhancement for bone grafts. *Oral Surg Oral Med Oral Pathol Oral Radiol Endod* 1998; **85**: 638-646.
37. Kumar RV, Shubhashini N. Platelet rich fibrin: a new paradigm in periodontal regeneration. *Cell Tissue Bank* 2013; **14**: 453-463.
38. Kang YH, Jeon SH, Park JY, Chung JH, Choung YH, Choung HW, Kim ES, Choung PH. Platelet-rich fibrin is a Bioscaffold and reservoir of growth factors for tissue regeneration. *Tissue Eng Part A* 2011; **17**: 349-359.
39. Schulz KF, Altman DG, Moher D, Group C. CONSORT 2010 Statement: updated guidelines for reporting parallel group randomised trials. *BMC Med* 2010; **8**: 18.

40. Faul F, Erdfelder E, Buchner A, Lang AG. Statistical power analyses using G*Power 3.1: tests for correlation and regression analyses. *Behav Res Methods* 2009; **41**: 1149-1160.
41. Zhang Y, Tangl S, Huber CD, Lin Y, Qiu L, Rausch-Fan X. Effects of Choukroun's platelet-rich fibrin on bone regeneration in combination with deproteinized bovine bone mineral in maxillary sinus augmentation: a histological and histomorphometric study. *J Craniomaxillofac Surg* 2012; **40**: 321-328.
42. de Molon RS, Sakakura CE, Faeda RS, Sartori R, Palhares D, Margonar R, Marcantonio E, Jr. Effect of the long-term administration of Cyclosporine A on bone healing around osseointegrated titanium implants: A histomorphometric study in the rabbit tibia. *Microsc Res Tech* 2017; **80**: 1000-1008.
43. de Molon RS, Morais-Camilo JA, Verzola MH, Faeda RS, Pepato MT, Marcantonio E, Jr. Impact of diabetes mellitus and metabolic control on bone healing around osseointegrated implants: removal torque and histomorphometric analysis in rats. *Clin Oral Implants Res* 2013; **24**: 831-837.
44. Pichotano EC, de Molon RS, Freitas de Paula LG, de Souza RV, Marcantonio E, Jr., Zandim-Barcelos DL. Early placement of dental implants in maxillary sinus grafted with leukocyte and platelet-rich fibrin (L-PRF) and deproteinized bovine bone mineral. *J Oral Implantol* 2018; **44**: 199-206.
45. Kotsakis GA, Boufidou F, Hinrichs JE, Prasad HS, Rohrer M, Tosios KI. Extraction Socket Management Utilizing Platelet Rich Fibrin: A Proof-of-Principle Study of the "Accelerated-Early Implant Placement" Concept. *J Oral Implantol* 2016; **42**: 164-168.

46. Jensen SS, Terheyden H. Bone augmentation procedures in localized defects in the alveolar ridge: clinical results with different bone grafts and bone-substitute materials. *Int J Oral Maxillofac Implants* 2009; **24 Suppl**: 218-236.
47. Hallman M, Thor A. Bone substitutes and growth factors as an alternative/complement to autogenous bone for grafting in implant dentistry. *Periodontol* 2000 2008; **47**: 172-192.
48. Inchingolo F, Tatullo M, Marrelli M, Inchingolo AM, Scacco S, Inchingolo AD, Dipalma G, Vermesan D, Abbinante A, Cagiano R. Trial with Platelet-Rich Fibrin and Bio-Oss used as grafting materials in the treatment of the severe maxillar bone atrophy: clinical and radiological evaluations. *Eur Rev Med Pharmacol Sci* 2010; **14**: 1075-1084.
49. Jeong SM, Lee CU, Son JS, Oh JH, Fang Y, Choi BH. Simultaneous sinus lift and implantation using platelet-rich fibrin as sole grafting material. *J Craniomaxillofac Surg* 2014; **42**: 990-994.
50. Marrelli M, Tatullo M. Influence of PRF in the healing of bone and gingival tissues. Clinical and histological evaluations. *Eur Rev Med Pharmacol Sci* 2013; **17**: 1958-1962.
51. Mazor Z, Horowitz RA, Del Corso M, Prasad HS, Rohrer MD, Dohan Ehrenfest DM. Sinus floor augmentation with simultaneous implant placement using Choukroun's platelet-rich fibrin as the sole grafting material: a radiologic and histologic study at 6 months. *J Periodontol* 2009; **80**: 2056-2064.
52. Oncu E, Alaaddinoglu EE. The effect of platelet-rich fibrin on implant stability. *Int J Oral Maxillofac Implants* 2015; **30**: 578-582.
53. Kirmeier R, Payer M, Wehrschuetz M, Jakse N, Platzer S, Lorenzoni M. Evaluation of three-dimensional changes after sinus floor augmentation with different grafting materials. *Clin Oral Implants Res* 2008; **19**: 366-372.

54. Klein GG, Curvello VP, Dutra RA, Simeao SP, Santos PL, Gulinelli JL, Filho HN. Bone Volume Changes After Sinus Floor Augmentation with Heterogenous Graft. *Int J Oral Maxillofac Implants* 2016; **31**: 665-671.
55. Kuhl S, Payer M, Kirmeier R, Wildburger A, Wegscheider W, Jakse N. The influence of bone marrow aspirates and concentrates on the early volume stability of maxillary sinus grafts with deproteinized bovine bone mineral - first results of a RCT. *Clin Oral Implants Res* 2014; **25**: 221-225.
56. Gultekin BA, Cansiz E, Borahan O, Mangano C, Kolerman R, Mijiritsky E, Yalcin S. Evaluation of Volumetric Changes of Augmented Maxillary Sinus With Different Bone Grafting Biomaterials. *J Craniofac Surg* 2016; **27**: e144-148.
57. Shanbhag S, Shanbhag V, Stavropoulos A. Volume changes of maxillary sinus augmentations over time: a systematic review. *Int J Oral Maxillofac Implants* 2014; **29**: 881-892.
58. Martinez H, Davarpanah M, Missika P, Celletti R, Lazzara R. Optimal implant stabilization in low density bone. *Clin Oral Implants Res* 2001; **12**: 423-432.
59. Xuan F, Lee CU, Son JS, Jeong SM, Choi BH. A comparative study of the regenerative effect of sinus bone grafting with platelet-rich fibrin-mixed Bio-Oss(R) and commercial fibrin-mixed Bio-Oss(R): an experimental study. *J Craniomaxillofac Surg* 2014; **42**: e47-50.
60. Le Guehennec L, Layrolle P, Daculsi G. A review of bioceramics and fibrin sealant. *Eur Cell Mater* 2004; **8**: 1-10; discussion 10-11.
61. Comert Kilic S, Gungormus M, Parlak SN. Histologic and histomorphometric assessment of sinus-floor augmentation with beta-tricalcium phosphate alone or in combination with pure-platelet-rich plasma or platelet-rich fibrin: A randomized clinical trial. *Clin Implant Dent Relat Res* 2017; **19**: 959-967.

62. Peker E, Karaca IR, Yildirim B. Experimental Evaluation of the Effectiveness of Demineralized Bone Matrix and Collagenated Heterologous Bone Grafts Used Alone or in Combination with Platelet-Rich Fibrin on Bone Healing in Sinus Floor Augmentation. *Int J Oral Maxillofac Implants* 2016; **31**: e24-31.
63. de Molon RS, Lages FS, Rivera CP, de Souza Faloni AP, Margonar R, Queiroz TP. Evaluation of Short and Regular Implants after Prosthesis Placement in the Mandible: A Nonrandomized Controlled Clinical Trial. *J Contemp Dent Pract* 2017; **18**: 1122-1129.
64. Sennerby L, Meredith N. Implant stability measurements using resonance frequency analysis: biological and biomechanical aspects and clinical implications. *Periodontol 2000* 2008; **47**: 51-66.
65. Sennerby L, Andersson P, Pagliani L, Giani C, Moretti G, Molinari M, Motroni A. Evaluation of a Novel Cone Beam Computed Tomography Scanner for Bone Density Examinations in Preoperative 3D Reconstructions and Correlation with Primary Implant Stability. *Clin Implant Dent Relat Res* 2015; **17**: 844-853.
66. Sennerby L, Pagliani L, Petersson A, Verrocchi D, Volpe S, Andersson P. Two different implant designs and impact of related drilling protocols on primary stability in different bone densities: an in vitro comparison study. *Int J Oral Maxillofac Implants* 2015; **30**: 564-568.
67. Balleri P, Cozzolino A, Ghelli L, Momicchioli G, Varriale A. Stability measurements of osseointegrated implants using Osstell in partially edentulous jaws after 1 year of loading: a pilot study. *Clin Implant Dent Relat Res* 2002; **4**: 128-132.

FIGURE LEGENDS

Figure 1. Flowchart of the experimental design.

Figure 2. Representative histological section from group DBBM + L-PRF **(a)** and only DBBM **(b)**. NB is native bone; NFL corresponds to the newly formed bone; B is biomaterial; and ST is soft tissue. Yellow color corresponds to the newly formed bone; red is biomaterial; Blue is native bone.

TABLE LEGENDS

Table 1. Patient demographics and clinical data.

Table 2. Graft volume measurements immediately after sinus augmentation (T1) and after a healing period of four months for the test (DBBM + L-PRF) and 8 months for the control (DBBM) group (T2).
the control group).

Table 3. Histomorphometric results after four months of healing for the test (DBBM + L-PRF) and 8 months for the control (DBBM) group.

Table 4. Implant stability quotient (ISQ) measured by means of resonance frequency analysis immediately after implant placement and at implant loading in both groups.