King's Research Portal

DOI:

[10.1007/978-1-4939-3530-7_15](https://doi.org/10.1007/978-1-4939-3530-7_15)

Document Version

Peer reviewed version

[Link to publication record in King's Research Portal](#)

Citation for published version (APA):

Minaisah, R-M., Cox, S., & Warren, D. T. (2016). The Use of Polyacrylamide Hydrogels to Study the Effects of Matrix Stiffness on Nuclear Envelope Properties. In *Methods in Molecular Biology* (Vol. 1411, pp. 233-9) https://doi.org/10.1007/978-1-4939-3530-7_15

Citing this paper

Please note that where the full-text provided on King's Research Portal is the Author Accepted Manuscript or Post-Print version this may differ from the final Published version. If citing, it is advised that you check and use the publisher's definitive version for pagination, volume/issue, and date of publication details. And where the final published version is provided on the Research Portal, if citing you are again advised to check the publisher's website for any subsequent corrections.

General rights

Copyright and moral rights for the publications made accessible in the Research Portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognize and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the Research Portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the Research Portal

Take down policy

If you believe that this document breaches copyright please contact librarypure@kcl.ac.uk providing details, and we will remove access to the work immediately and investigate your claim.

The use of polyacrylamide hydrogels to study the effects of matrix stiffness on nuclear envelope properties

Rose-Marie Minaisah¹, Susan Cox² and Derek T Warren¹

1. British Heart Foundation Centre of Research Excellence, Cardiovascular Division, King's College London, UK. SE5 9NU

2. Randall Division of Cell and Molecular Biophysics, New Hunt's House, King's College London, UK. SE1

+Corresponding author: Dr. Derek Warren
King's College London
Cardiovascular Division,
James Black Centre,
125 Coldharbour Lane,
London SE5 9NU.
UK.

Tel: +44 020 7848 5222

Fax: +44 020 7848 5193

Email: derek.warren@kcl.ac.uk

Running Head: Culture Conditions on Nuclear Envelope Composition

i. Summary

Matrix-derived mechanical cues influence cell proliferation, motility and differentiation. Recent findings clearly demonstrate that the nuclear envelope (NE) adapts and remodels in response to mechanical signals, including matrix stiffness, yet a plethora of studies have been performed on tissue culture plastic or glass that have a similar stiffness to cortical bone. Using methods that allow modulation of matrix stiffness will provide further insight into the role of the NE in physiological conditions and the impact of changes in stiffness observed during ageing and disease on cellular function. In this chapter, we describe the polyacrylamide hydrogel system, that allows fabrication of hydrogels with variable stiffness to better mimic the environment experienced by cells in most tissues of the body.

ii. Key Words

Mechanotransduction, hydrogels, extracellular matrix and stiffness

1.Introduction

Signals derived from the extracellular microenvironment regulate many cellular processes including proliferation, migration and differentiation. Our understanding of how cells sense and transmit these signals has increased rapidly in recent years and we are now beginning to appreciate the role of biophysical signalling, in addition to biochemical pathways that regulate these processes. Matrix stiffness has emerged as a major regulator of cellular behaviour and the stiffness of the microenvironment transmits 'outside-in' forces to cells. This process is dependent on ECM adhesions that convey force between the ECM and cytoskeleton[1]. Cells respond to outside-in signals by exerting actomyosin-based contractile forces on the matrix (inside-out forces) that increase cell stiffness and scale with ECM stiffness[2]. Rho/ROCK signalling is rapidly activated at ECM adhesions in response to matrix stiffness to augment actomyosin activity, via actin polymerisation and myosin light chain phosphorylation, and increase cell stiffness[3,4].

The nuclear envelope (NE) consists of an outer nuclear membrane (ONM) and an inner nuclear membrane (INM) with both membranes joined at nuclear pores[5]. Importantly, the NE has emerged as a major regulator of cytoskeletal organisation and differentiation[6]. Underlying the INM is an intermediate filament (IF) protein meshwork, called the nuclear lamina, which is composed of lamins (A/C and B) and lamina associated proteins[5]. The nuclear lamina is indirectly coupled to the cytoskeleton via the Linker of Nucleoskeleton and Cytoskeleton (LINC) complex that spans the NE[7,8]. This complex is comprised of nesprin and SUN family members. Giant nesprin-1/2 isoforms reside on the ONM and bind F-actin via a pair of N-terminal Calponin Homology (CH) domains[9]. Complex stability is maintained

via interactions between the C-terminal Klarsicht, Anc-1, Syne-1 Homology (KASH) domain of the nesprins and the SUN domain of SUN1 and SUN2 in the perinuclear space[7,8]. SUN1/2 span the INM and interact directly with lamins A/C, physically coupling the actin cytoskeleton to the nuclear lamina[8]. Thus, the plasma membrane, actin cytoskeleton and nucleus function as a single mechanically coupled system. Recent studies have highlighted the importance of this network in matrix-derived mechanosignalling and lamin A levels scale with matrix stiffness in mesenchymal stem cells (MSCs)[10,11]. Lamin A also modulates actin dynamics to control the nuclear availability of the serum response factor (SRF)-coactivator myocardin-related transcription factor-A (MRTF-A) to regulate SRF mediated transcription[12]. Importantly, the LINC complex has recently been shown to directly transmit biophysical mechanical signals across the NE and mechanical stimulation of nesprin-1 giant on the ONM increases lamin A coupling to the INM[13].

The Young's modulus, E (a measure of material stiffness), of different tissues within the body demonstrates considerable variation, from very soft (fat 0.1-1kPa), to stiff (muscle 10-20kPa), to extremely stiff (cortical bone 10-20GPa)[14]. Moreover, ageing and disease augment tissue stiffness. For example, healthy aorta has a Young's modulus of between 10-20kPa, whereas atherosclerotic plaques contain a stiffened fibrous cap ($E=60-250\text{kPa}$) and aortas from spontaneously hypertensive rats display a 2-4 fold increase in stiffness compared to age-matched controls[15-18]. A plethora of studies have been performed on tissue culture plastic ($E=10\text{GPa}$) and glass ($E=55\text{GPa}$) that possess a similar Young's modulus to cortical bone ($E=10-20\text{GPa}$). However, following recent advances in our understanding of how the NE adapts and remodels in response to matrix-derived mechanical cues, methods that allow manipulation of these signals will provide a better understanding of NE

function in physiological and pathological conditions. One strategy to regulate ECM stiffness is via the utilisation of hydrogels that possess defined Young's moduli. Polyacrylamide (PA) hydrogels have a number of advantages including: 1) no specialised equipment is required for fabrication, 2) they possess constant surface chemistry despite altered mechanical properties and 3) only ECM molecules covalently linked to the hydrogel can serve as ligands for cell attachment[14,19]. In this chapter, we will discuss the process of PA hydrogel fabrication, a multistep process that includes coverslip activation, hydrogel polymerisation and hydrogel functionalisation.

2.Materials

(3-aminopropyl)-triethoxysilane (APES)

0.5% glutaraldehyde

Ammonium persulphate (APS), 10% dissolved in water

N,N,N,N' tetramethyl-ethylenediamine (TEMED)

Sulfo-SANPH, 1mg/ml in water

2.5% bis-acrylamide

40% acrylamide

Phosphate buffered saline (PBS)

Earle's balanced salt solution

30mm thickness No 1 coverslip

1mm thick glass slide

6-well culture plate

Collagen-1 (or ECM component of choice)

A trans-illuminator or UV lamp that irradiates at 300-460nm. We use a 25W UVP trans-illuminator.

3.Method

All steps are performed at room temperature, unless otherwise stated.

3.1 Coverslip activation

1. In a fume hood, cover the top surface of a 30mm coverslip with APES for 5 min.
2. Rinse 3 times with 2 mL distilled water, making sure that the top and bottom surfaces of the coverslip are well washed (see**Note 1**).
3. Immerse coverslips in 0.5% glutaraldehyde solution and incubate for 30-60 min.
4. Rinse 3 times with distilled water and air dry. In our hands, activated coverslips remain functional for 1 week and can be stored at room temperature.

3.2 Hydrogel preparation

1. Mix together the appropriate ratios of acrylamide and bis-acrylamide in distilled water or PBS. Typical ratios that we use, and their corresponding Young's moduli (determined by atomic force microscopy), are shown in Table 1 (see**Note 2**). The Young's moduli of other acrylamide/bis-acrylamide ratios can be found elsewhere[14] (see**Note3**).

2. To initiate hydrogel polymerisation, add 1:100 APS and 1:1000 TEMED to the aliquot of stock solution and mix well (see**Note 4**).
3. Place 50µl of the mix in the centre of a glass slide. Place the activated side of the coverslip into the solution, gently lowering the coverslip and being careful not to create air bubbles. Incubate for 5-10 min, using any leftover mix to assess polymerisation state (see**Note 5**).
4. Remove the glass slide and place the coverslip, hydrogel side up, into the bottom of a 6-well plate or 35mm petri dish (see**Note 6**).
5. Wash hydrogels with distilled water to remove any unpolymerised mixture. Hydrogels can be stored in distilled water or PBS at 4°C for 1 week.

3.3 Functionalising hydrogels for tissue culture

Cell attachment to the hydrogels requires an ECM coating. We use collagen, however, you can use any ECM component, depending on cell type and integrin pathways of interest. The ECM component is covalently cross-linked to the hydrogel and to achieve this we use sulfo-SANPH, a photo-activated protein cross-linker using the following method.

1. Remove the distilled water/PBS from the hydrogel.
2. Add 500-1000 µl of sulfo-SANPH, making sure the hydrogel is fully immersed to allow complete coverage (see**Note 7**).
3. Expose to 365nm UV light for 5-10 min. The hydrogel will be coated in dark red sulfo-SANPH. Repeat if necessary (see**Note 8**).

4. Remove the sulfo-SANPH and wash the hydrogel 3x in sterile PBS (see**note 9**).
5. Immerse the coverslip in 0.1-0.3mg/ml collagen or ECM component of your choice. Incubate at 4°C for between 1-4 hours (see**Note 10**).
6. Wash once in PBS and then incubate in prewarmed Earle's balanced salt solution (or equivalent) for 10-30 min at 37°C to allow the hydrogel to warm up (see**Note 11**).
7. Plate cells onto the hydrogel in their standard medium (see**Note 12**). A schematic of the final functionalised hydrogel set-up is shown in Figure 1.
8. Cells can be trypsinised and maintained on hydrogels for weeks.

4. Notes

1. It is important to wash well as any remaining APES will react with glutaraldehyde in subsequent steps leaving a brown material that could interfere with downstream experiments.
2. For mapping of cellular traction forces, fluorescent beads may be added to the hydrogel.
3. We use hydrogels that mimic the physiological and pathological stiffness experienced by VSMCs and fibroblasts. The choice of hydrogel stiffness is cell type dependent and should approximate conditions experienced *in vivo*.
4. For consistency between batches of hydrogels, we prepare a 50ml stock solution and perform atomic force microscopy (AFM) to confirm the Young's modulus of each stock. Solutions can be stored at 4°C for several months.

5. Extended polymerisation times can make it difficult to remove the coverslip from the slide.
6. Trying to lift the coverslip directly off the slide often results in snapping of the coverslip. To overcome this, we first slide the coverslip and then lift.
7. As sulfo-SANPH is light sensitive it should be made fresh and kept in the dark until required.
8. UV exposure makes the sulfo-SANPH change to a dark red colour. If this does not happen, then cross-linking has failed and the step needs to be repeated.
9. Perform all subsequent steps in a tissue culture hood to limit the chance of contamination.
10. We incubate for 1 hour but this may need to be increased, depending on cell type. The ECM coating will contribute to the overall stiffness of the functionalised hydrogel so it is important to keep the concentration of ECM component and the incubation time consistent. It is also important to confirm the functionalised hydrogel stiffness to confirm the ECM coat is not altering overall stiffness.
11. We find warming the hydrogel yields better cell attachment/viability.
12. Seeding number is cell size and assay dependent. For example, we aim for a confluency of between 60-70% for Western blotting whereas for immunofluorescence we aim for 20-30% confluency so that the cells are not touching one another. In our hands, confluent vascular smooth muscle cell (VSMC) and fibroblast cultures detach from the hydrogel.

Acknowledgements

This work is supported by a British Heart Foundation (BHF) Intermediate Basic Science Research Fellowship awarded to DW (FS/11/53/29020).

5. References

1. Ankam S, Suryana M, Chan LY, Moe AA, Teo BK, Law JB, Sheetz MP, Low HY, Yim EK (2013) Substrate topography and size determine the fate of human embryonic stem cells to neuronal or glial lineage. *Acta Biomater* 9 (1):4535-4545. doi:10.1016/j.actbio.2012.08.018
2. Etienne J, Fouchard J, Mitrossilis D, Bufi N, Durand-Smet P, Asnacios A (2015) Cells as liquid motors: mechanosensitivity emerges from collective dynamics of actomyosin cortex. *Proc Natl Acad Sci U S A* 112 (9):2740-2745. doi:10.1073/pnas.1417113112
3. Beningo KA, Hamao K, Dembo M, Wang YL, Hosoya H (2006) Traction forces of fibroblasts are regulated by the Rho-dependent kinase but not by the myosin light chain kinase. *Arch Biochem Biophys* 456 (2):224-231. doi:10.1016/j.abb.2006.09.025
4. Huang X, Yang N, Fiore VF, Barker TH, Sun Y, Morris SW, Ding Q, Thannickal VJ, Zhou Y (2012) Matrix stiffness-induced myofibroblast differentiation is mediated by intrinsic mechanotransduction. *Am J Respir Cell Mol Biol* 47 (3):340-348. doi:10.1165/rcmb.2012-0050OC
5. Burke B, Ellenberg J (2002) Remodelling the walls of the nucleus. *Nat Rev Mol Cell Biol* 3 (7):487-497. doi:10.1038/nrm860
6. Mellad JA, Warren DT, Shanahan CM (2011) Nesprins LINC the nucleus and cytoskeleton. *Curr Opin Cell Biol* 23 (1):47-54. doi:10.1016/j.ceb.2010.11.006
7. Crisp M, Liu Q, Roux K, Rattner JB, Shanahan C, Burke B, Stahl PD, Hodzic D (2006) Coupling of the nucleus and cytoplasm: role of the LINC complex. *J Cell Biol* 172 (1):41-53. doi:10.1083/jcb.200509124
8. Haque F, Lloyd DJ, Smallwood DT, Dent CL, Shanahan CM, Fry AM, Trembath RC, Shackleton S (2006) SUN1 interacts with nuclear lamin A and cytoplasmic nesprins to provide a physical connection between the nuclear lamina and the cytoskeleton. *Mol Cell Biol* 26 (10):3738-3751. doi:10.1128/MCB.26.10.3738-3751.2006
9. Zhang Q, Ragnauth CD, Skepper JN, Worth NF, Warren DT, Roberts RG, Weissberg PL, Ellis JA, Shanahan CM (2005) Nesprin-2 is a multi-isomeric protein that binds lamin and emerin at the nuclear envelope and forms a subcellular network in skeletal muscle. *J Cell Sci* 118 (Pt 4):673-687. doi:10.1242/jcs.01642
10. Swift J, Ivanovska IL, Buxboim A, Harada T, Dingal PC, Pinter J, Pajerowski JD, Spinler KR, Shin JW, Tewari M, Rehfeldt F, Speicher DW, Discher DE (2013) Nuclear lamin-A scales with tissue stiffness and enhances matrix-directed differentiation. *Science* 341 (6149):1240104. doi:10.1126/science.1240104
11. Buxboim A, Swift J, Irianto J, Spinler KR, Dingal PC, Athirasala A, Kao YR, Cho S, Harada T, Shin JW, Discher DE (2014) Matrix elasticity regulates lamin-A,C phosphorylation and turnover with feedback to actomyosin. *Curr Biol* 24 (16):1909-1917. doi:10.1016/j.cub.2014.07.001
12. Ho CY, Jaalouk DE, Vartiainen MK, Lammerding J (2013) Lamin A/C and emerin regulate MKL1-SRF activity by modulating actin dynamics. *Nature* 497 (7450):507-511. doi:10.1038/nature12105

13. Guilluy C, Osborne LD, Van Landeghem L, Sharek L, Superfine R, Garcia-Mata R, Burridge K (2014) Isolated nuclei adapt to force and reveal a mechanotransduction pathway in the nucleus. *Nat Cell Biol* 16 (4):376-381. doi:10.1038/ncb2927
14. Tse JR, Engler AJ (2010) Preparation of hydrogel substrates with tunable mechanical properties. *Curr Protoc Cell Biol Chapter 10:Unit 10 16*. doi:10.1002/0471143030.cb1016s47
15. Sehgel NL, Sun Z, Hong Z, Hunter WC, Hill MA, Vatner DE, Vatner SF, Meininger GA (2015) Augmented vascular smooth muscle cell stiffness and adhesion when hypertension is superimposed on aging. *Hypertension* 65 (2):370-377. doi:10.1161/HYPERTENSIONAHA.114.04456
16. Sehgel NL, Zhu Y, Sun Z, Trzeciakowski JP, Hong Z, Hunter WC, Vatner DE, Meininger GA, Vatner SF (2013) Increased vascular smooth muscle cell stiffness: a novel mechanism for aortic stiffness in hypertension. *Am J Physiol Heart Circ Physiol* 305 (9):H1281-1287. doi:10.1152/ajpheart.00232.2013
17. Tracqui P, Broisat A, Toczek J, Mesnier N, Ohayon J, Riou L (2011) Mapping elasticity moduli of atherosclerotic plaque in situ via atomic force microscopy. *J Struct Biol* 174 (1):115-123. doi:10.1016/j.jsb.2011.01.010
18. Hayenga HN, Trache A, Trzeciakowski J, Humphrey JD (2011) Regional atherosclerotic plaque properties in ApoE^{-/-} mice quantified by atomic force, immunofluorescence, and light microscopy. *J Vasc Res* 48 (6):495-504. doi:10.1159/000329586
19. Cretu A, Castagnino P, Assoian R (2010) Studying the effects of matrix stiffness on cellular function using acrylamide-based hydrogels. *J Vis Exp* (42). doi:10.3791/2089

Table 1

Hydrogel stiffness (kPa)	Acrylamide (final %)	Bis-acrylamide (final %)
1.879 +/- 0.2835	5	0.1
11.78 +/- 1.270	7.5	0.15

Figure legend

Figure 1. Schematic diagram representing the final functionalised hydrogel set-up with cells attached.

Figure 1. Schematic diagram representing the final functionalised hydrogel set up with cells attached.